

Cutting data recommendations for solid carbide drills

Feed and cutting speed

MEGA-Speed-Drill-Uni | SCD221

MMG*		Workpiece material	Strength/hardness [N/mm ²] [HRC]		Cutting speed v _c [m/min]				Feed f [mm] for drill diameter					
Internal cooling	External cooling	MQL	Air	3.00	4.50	6.50	9.50	14.00	20.00					
P	P1.1	Structural, free-cutting, case hardened and heat-treated steels, non-alloy	< 700		170	155	155		0.11	0.14	0.18	0.23	0.30	0.36
	P1.2	Structural, free-cutting, case hardened and heat-treated steels, non-alloy	< 1,200		155	130	130		0.14	0.18	0.22	0.29	0.37	0.45
	P2.1	Nitrided, case hardened and heat-treated steels, alloy	< 900		170	145	145		0.13	0.17	0.21	0.27	0.35	0.43
	P2.2	Nitrided, case hardened and heat-treated steels, alloy	< 1,400		120	100	100		0.11	0.14	0.17	0.22	0.28	0.34
	P3.1	Tool, bearing, spring and high-speed steels**	< 800		130	110	110		0.11	0.15	0.19	0.25	0.32	0.38
	P3.2	Tool, bearing, spring and high-speed steels**	< 1,000		115	100	95		0.10	0.14	0.17	0.22	0.28	0.35
P	P3.3	Tool, bearing, spring and high-speed steels**	< 1,500		100	75	85		0.10	0.13	0.16	0.20	0.26	0.31
	P4.1	Stainless steels, ferritic and martensitic			100	75	85		0.08	0.10	0.13	0.16	0.21	0.25
	P5.1	Cast steel			170	145	145		0.13	0.17	0.21	0.27	0.35	0.43
	P6.1	Stainless cast steel, ferritic and martensitic			100	75	85		0.08	0.10	0.13	0.16	0.21	0.25
	K1.1	Cast iron with lamellar graphite (grey cast iron), GJL	< 300		150	105	105	105	0.13	0.19	0.26	0.35	0.45	0.54
	K2.1	Cast iron with spheroidal graphite, GJS	< 500		200	125	150	150	0.13	0.18	0.25	0.33	0.42	0.50
K	K2.2	Cast iron with spheroidal graphite, GJS	≤ 800		125	95	95		0.12	0.16	0.22	0.28	0.36	0.43
	K2.3	Cast iron with spheroidal graphite, GJS	> 800		75	50	65		0.09	0.12	0.15	0.19	0.24	0.28
K3	K3.1	Cast iron with spheroidal graphite, GJV; malleable cast iron, GJM	< 500		115	100	100		0.13	0.18	0.23	0.31	0.39	0.46
	K3.2	Cast iron with spheroidal graphite, GJV; malleable cast iron, GJM	> 500		100	90	90		0.11	0.15	0.19	0.25	0.31	0.36

* MAPAL machining groups

** If the alloy parts Cr, Mo, Ni, V, W in total > 8% then select the next highest MAPAL machining group.

The specified cutting values are guide values.

The optimum data for the respective machining task should be determined during the test or machining.